

Safety/Anti-Fatigue Floor Mat



Test	Test Description	*Results
-	Compression Deflection	@ 20 lbs./in ² : 0.449 in. @ 40 lbs./in ² : 0.626 in.
ATSM D3884-01	Abrasion Resistance (Measured in weight loss)	@500 cycles: 1.44 Grams (4.1%) @1000 cycles: 7.62 Grams (21.9%)
ASTM C-1028	Static Coefficient of Friction	Dry: 0.83 Wet: 0.79
ASTM D-1004-94a-03	Tear Resistance (Measured in Ibs.)	15.0 lbs.
ASTM D-412	Breaking Load & Elongation (Avg.)	Breaking Load: 28.5lbs./in ² Elongation: 74%

*Testing performed by an independent test laboratory.



8/2014



Custom

• Thickness: 1/2"

- Materials: PVC Sponge
- Stock Sizes: 2' x 3', 2' x 6', 3' x 4', 3' x 5', 3' x 6', 3' x 12'
- Roll Sizes: 2' x 60', 3' x 60', 4' x 60'
- Custom sizes in 2', 3', and 4' widths (up to 60')

